RG104 E-1 Box 121

1880

Weekly Report of Gold Deposits Melted at United States Mint.

Date.	Assay No.	Name of Depositor.	Weight before Melting. OZ.	DEC.	Weight after Melting. OZ.	DEC.	Loss. OZ.	DEC.	Loss per ct.		Gain. OZ.	DEC.	Description of Bullion.	Notes of Melter & Refiner. 10/3/80
March 1st	402	G. C. Thompson	5	18	5	16		02		40			Melted Lps, Va.	The deposits are from
	3	do	13	46	10	36	3	10	23	84			Jewelry & Hitch Cases	the following sources:
	4	do	15	40	10	38	5	02	33	47			Button & Bar, Base	Virginia (1) 1
	5	Harry Pratt	11	95	11	90		05		67			Buttons	N. Carolina (1) 2
	6	N. C. Strayne	76	00	74	44	1	56	2	05			Button	N. Mexico 1
	7	N. R. Lee	73	40	73	38		02		03			Bar	California 1
	8	C. R. Jones	20	51	15	82	4	69	22	33			Leaf	Colorado (Mint)(1) 1
	9	G. H. Smith	5	88	5	67		21	3	50			Amt & Gra, N. C.	Australia 1
	10	Richd Helms	26	86	26	86							U. S. Coin	Finer bullion (3) 9
	1	John Sherry	3	53	3	53							Button	Base 2
2nd	2	G. C. Thompson	157	09	145	38	8	67	5	63			Bars	Jewelry & Base 6
	3	Morgan & Heady	70	59	59	27	11	32	15	94			Strips	very base 6
	4	Hagstoz & Thorp	218	16	216	64	1	52		70			Bar	Dental Plate 2
3rd	5	G. C. Thompson	15	84	13	63	2	21	13	81			Jewelry, Co & Silver	Coin 5
	6	do	78	80	63	60	15	20	19	24			Jewelry	Total 37
	7	A. Losse	14	07	13	79		28	2	00			Pb & Fillings	
	8	Jas. Mason	3	44	3	35		09	3	00			Lps, Australia	The losses on the mixt
	9	G. C. Thompson	11	88	8	18	3	70	30	83			Rings, Base	bullion from N. Carolina
	30	Phillips & Jacobs	53	73	53	73							U. S. Coin	3½%; from N. Mexico
	1	Jacob Riegel	10	58	10	32		26	2	36			Amt, Grs & Lps, N. M.	2.36%; & from
	2	F. H. Teal	13	42	13	10		32	2	46			Pb, Filings & Fillings	Australian lumps
	3	Ph. L. McDonald	11	82	9	17	2	65	22	08			Crushed Quartz, Cal.	3.% ; are all legit
	4	A. Loudon Snowden, Supt.	52	81	52	79		02		04			Bars, U. S. A. U. N. C.	imate; — the heavy
4th	5	G. C. Thompson	37	23	37	18		05		14			Buttons	loss on the California
	6	do	4	32	4	30		02		50			Hitch Case	quartz, 22.08%, is
	7	do	4	58	4	10		58	11	60			Jewelry	due to that quartz.
	8	McCall & Newman	70	05	69	93		12		17			Bar	The loss on 12 deposits
	9	P. S. Gallowell	5	02	5	02							Buttons	of finer bullion, 22%,
	30	H. A. Shäfer & Bro.	42	47	38	48	3	99	9	50			Rings, Base	is very low; — on the
	1	G. A. C. Rosenthal	18	71	14	52	4	19	22	05			Button, Base	base, 3.84%, is mod-
	2	H. H. Shäfer & Bro.	26	86	26	86							U. S. Coin	erate; — on jewelry
5th	3	L. R. Ford	26	28	24	94	1	34	5	15			Hitch Cases & Jewelry	& Cases, 15.62%, is a
	4	A. Loudon Snowden, Supt.	331	15	331	15							Bars, U. S. Mint, Denver	fair average; —
6th	5	G. C. Thompson	34	04	27	42	6	62	19	47			Hitch Cases & Jewelry	on very base, 22.35%
	6	H. Muhr's Sons	16	64	16	64							Bars	is rather lower than
	7	J. C. Meeks	26	86	26	86							U. S. Coin	usual; on dental
	8	Richd Helms	26	86	26	86							U. S. Coin	plate, 2.23%, is full;
			1632	46	1554	61	77	85	6	98				— on coin no loss, is
														too little, especially
														on 5 deposits.
														J. P. C. Booth
														M. & R.

For week ending March 6th 1880
Approximate value, $24,096.45

S. Notley Dunglison

To the Director of the Mint.

Register.

RG104 E-1 Box 121

Report of Gold Deposits
called for week ending
March 6th 1880

NARA RG104, Entry 1, Box 121

[Abstract:] Report of Gold Deposits melted for week ending March 6, 1880

Weekly Report of Gold Deposits Melted at United States Mint.

[Please see original images for data table.]